



## Intergrain UltraDeck over GRM / Biowood composite timber

Intergrain UltraDeck is an extremely long lasting, water based oil for decking and exterior timber. UltraDeck contains unique Hydroguard technology™ which adds significant protection to guard exterior timber against Australia's harsh natural conditions as well as the abrasive effects of foot traffic. The natural-looking finish resists stain absorption and dirt settle, helping timber stay clean. The result is timber that stays protected and looking fresh for significantly longer than traditional decking oils. UltraDeck is available in a lightly pigmented natural colour or with mild timber tones to highlight the characteristics of popular timber species. More colour tones can be achieved by tinting UltraDeck at the paint counter. UltraDeck is fast drying - allowing two coats to be applied in one day, and will weather naturally, without risk of cracking, blistering and peeling.

UltraDeck has been tested for use on GRM/Biowood composite timber, and has shown excellent adhesion and performance properties. UltraDeck is the recommended coating for all GRM/Biowood exterior composite timber.

### Colour recommendations

- For GRM/Biowood products in the colours Spotted Gum, Teak and Deep Walnut, we recommend using UltraDeck Natural.
- For GRM/Biowood products in the colours Red Cedar and Red Makassar, we recommend using UltraDeck Jarrah.
- For GRM/Biowood products in the colour Weather Wood, we recommend using UltraDeck Weather Wood/Grey.

## Application and Maintenance of Intergrain UltraDeck

### Surface Preparation

- Remove surface dirt by sweeping or washing down with water.
- Shake Intergrain Reviva thoroughly. Mix ONE (1) part Reviva to FOUR (4) parts water in a plastic container.

**PRECAUTION:** Avoid contact with painted or metal surfaces and vegetation. Protect using plastic sheeting. Rinse off thoroughly if contact occurs.

- Apply Reviva mixture generously to the timber with a stiff bristle brush, broom or scouring pad. Scrub the timber vigorously. Clean complete sections at one time. Spot cleaning should be avoided to prevent patchy results.
- Leave mixture on the timber for 10-15 minutes. If necessary, apply more mixture to keep timber damp throughout this period. For best results Reviva should be applied to cool surfaces, out of direct sunlight, to avoid the cleaner drying on the timber.
- Rinse off thoroughly using maximum pressure from a garden hose or using a high pressure water cleaner. A high pressure water cleaner is recommended for large areas.

Allow timber to dry thoroughly.

This document and any following pages are intended solely for the individual(s) and entity(s) named. They are confidential and may contain legally privileged information. The use, copying or distribution of them or any information they contain, by anyone other than the addressee, is prohibited. If you have received this document in error, please let us know by telephone or fax so we can arrange for its return. Thank you.



## Intergrain UltraDeck over GRM / Biowood composite timber

### Application

- Stir Intergrain UltraDeck thoroughly before and during use with a flat blade stirrer. Do not thin. If project requires more than one can of UltraDeck, mix all cans together in one large container to achieve colour uniformity.
- Apply UltraDeck using a quality brush, lambswool applicator, or spray (HVLP or airless). Do not apply by roller. If spraying, back-brush immediately after each section is coated to ensure a uniform finish.
- Do not overspread or apply thinly as insufficient film thickness will result in lap marks and compromise performance and durability. Take care to apply sufficient product to edges and end grain.
- When coating large areas, such as decking and weatherboards, coat no more than three boards at a time. Complete an entire length or continue until a natural break such as a window occurs.
- Wait four (4) hours to dry and apply a second coat.
- Three coats will be required in extreme conditions such as full sun exposure, around pools and in humid areas.

For a slip resistant coating on stairs, ramps and wet areas, add Intergrain UltraGrip additive into each coat of UltraDeck. Addition rate is 5% UltraGrip into UltraDeck.  
When using UltraGrip, do not apply by spray.

### Maintenance

- Conduct a routine 12 monthly maintenance inspection.
- Best protection of the timber and ease of maintenance is ensured if UltraDeck is recoated before deterioration of the coating and timber underneath occurs.
- First indication of the need for recoating will be observed as patchiness or discolouration on edges and areas where insufficient product has been applied.
- To apply a maintenance coat to a surface which is in good condition, simply clean the surface with Reviva and apply one coat of UltraDeck.

### Coverage

14 square metres per litre.

### Drying and Recoat Times

- All timings quoted at 25°C and 50% humidity. Drying and recoat times will be retarded by cold or humid conditions.
- Decking can be walked on after 12 hours, but may retain some tackiness for several days.
- Full curing 7 days.

### Precautions

- Do not apply in temperatures above 35°C or below 10°C or if rain or dew is expected within 4 hours of application.
- Do not apply to hot surfaces or in direct sunlight, as doing so will result in difficult application, poor adhesion and blistering.

Refer to product label or datasheet for more information.

Issue Date	4/12/2012
------------	-----------

This document and any following pages are intended solely for the individual(s) and entity(s) named. They are confidential and may contain legally privileged information. The use, copying or distribution of them or any information they contain, by anyone other than the addressee, is prohibited. If you have received this document in error, please let us know by telephone or fax so we can arrange for its return. Thank you.